

ARITEX NV – aristide
Nachtegaelstraat 109
2550 KONTICH



Your notice of	Your reference	Date
23-01-2012	12-003	10-02-2012

Analysis Report 12.00311.01

Required tests :

BS 5852 (2006)

Clause 11 (upholstery composite) - Assessment of the ignitability
of upholstered seating - crib ignition source no. 5

Identification number	Information given by the client	Date of receipt
T1200797	CABRO	23-01-2012

Pros Van Hoeyland

Order responsible

This report runs to 3 pages and may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.

The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

VAT BE 0459.218.289

Fin. Acc. 210-0472965-45

IBAN BE44 2100 4729 6545

CENTEXBEL-GENT
Technologiepark 7
BE-9052 Zwijnaarde
Tel. + 32 9 220 41 51 • Fax + 32 9 220 49 55
e-mail gent@centexbel.be

CENTEXBEL-BRUSSELS
Montoyerstraat 24 B2
BE-1000 Brussels
Tel. + 32 2 287 08 30 • Fax + 32 2 230 68 15

Reference: T1200797 - CABRO

Clause 11 (upholstery composite) - Assessment of the ignitability of upholstered seating - crib ignition source no. 5

Date of ending the test	10-02-2012
Standard used	BS 5852 (2006)
Deviation from the standard	-
Conditioning	23°C, relative humidity 50%

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test ; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Water soaking of the cover	No
Filling	F 35140 (Recticel) * - fire retardant foam - \pm 35 kg/m ³

* The filling complies with schedule 1 part 1 of the UK Furniture and Furnishings (Fire) (Safety) Regulations 1988

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Smoke, heat or glowing more than 1 hour	no	no
Smoulders more than 100 mm from source	no	no
Flaming criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Flames to extremities	no	no
Flames through thickness	no	no
Flame time > 10 min	no	no
Flame time	2 min 50 s	2 min 53 s
	non-ignition - NI/5	non-ignition - NI/5

Conclusion

Non-ignition - NI/5