

ARITEX
Nachtegalstraat 109
2550 KONTICH

your delivery of
2005-10-28

your reference

our reference
PVH.DVB/10231

date
Zwijnaarde, 2005-11-16

Analysis Report 48314/F

Required tests :

IMO Fire Test Procedures (1993) - Resolution A.652(16) - 1989
Recommendation on fire test procedures for upholstered furniture
smouldering cigarette test + butane flame test

Identification number	Information given by the client	Date of receipt
T511159	CABRO	2005-11-02

Pros Van Hoeyland
order responsible

For further information, please contact our sectorial adviser Pros Van Hoeyland

This report runs to 3 pages and may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel. The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.




VAT BE 0459.218.289
CENTEXBEL-GENT
Technologiepark 7
BE-9052 Zwijnaarde
Tel. + 32 9 220 41 51 • Fax + 32 9 220 49 55
e-mail gent@centexbel.be

Fin. Acc. 210-0472965-45

IBAN BE44 2100 4729 6545

CENTEXBEL-BRUSSELS
Montoyerstraat 24 B2
BE-1000 Brussels
Tel. + 32 2 287 08 30 • Fax + 32 2 230 68 15



Reference : T511159 - CABRO

IMO Fire Test Procedures (1993) - Resolution A.652(16) - 1989
Recommendation on fire test procedures for upholstered furniture - smouldering cigarette test

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test ; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

End of tests: 15 November 2005

A. Materials tested

Cover	:	- quality	CABRO
		- water soaking	no
Filling	:	- quality	T 23140 (Recticel) *
		- density	± 22 kg/m ³


* standard non-FR PU-foam (as indicated in Appendix A)

B. Smouldering cigarette test

	test nr. 1	test nr. 2
- flaming	no	no
- glowing	no	no
- smouldering > 60 min	no	no
- escalating flaming combustion	no	no
- escalating smouldering combustion	no	no
- remarks	/	/
	<u>non-ignition</u>	<u>non-ignition</u>

Conclusion: non-ignition

Performed under accreditation in the fire lab under the responsibility of Pros Van Hoeyland.



Reference : T511159 - CABRO

IMO Fire Test Procedures (1993) - Resolution A.652(16) - 1989
Recommendation on fire test procedures for upholstered furniture - butane flame test

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test ; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

End of tests: 15 November 2005

A. Materials tested

- | | | | | |
|---------|---|---|---------------|------------------------|
| Cover | : | - | quality | CABRO |
| | | - | water soaking | no |
| Filling | : | - | quality | T 23140 (Recticel) * |
| | | - | density | ± 22 kg/m ³ |

* standard non-FR PU-foam (as indicated in Appendix A)

B. Butane flame test

flame application time : 20 s

	test nr. 1	test nr. 2
- afterflame time (s)	1	1
- afterglow time (s)	0	0
- smouldering	no	no
- remarks	/	/
	<u>non-ignition</u>	<u>non-ignition</u>

Conclusion: non-ignition

Performed under accreditation in the fire lab under the responsibility of Pros Van Hoeyland.