

Ordernumber : 201506491
Date of order : 22-10-2015
Your reference : Schriftelijke aanvraag

Aristide nv
Nachtegaalstraat 109
2550 Kontich

Description : Leatherlook

SAMPLE
20150649101

Your reference : **CABRO 01 CAMEL**

Date of receipt : 22-10-2015

Sampling by : third party

Date analyses : Week 41-44 - 45

Place analyses : Servaco

Martindale abrasion ISO 5470-2: 2003 method 1 - dry to standardwool

Method : twmarl Atmosphere for conditioning and testing: 20° C ± 2° - 65 % RV ± 4 %, pressure : 12 kPa

Assessment to ISO 5470-2

1600 rubs	0 rating scale
3200 rubs	0 rating scale
6400 rubs	1 rating scale
12800 rubs	1 rating scale
25600 rubs	1 rating scale
38400 rubs	1 rating scale
51200 rubs	1 rating scale

Rub Fastness Veslic ISO 11640

Method : twves

felt dry	1.000 rubs: slight stainin - grade 4/5 no damage of the coating - colour 5
felt wet	1.000 rubs: slight stainin - grade 4/5 no damage of the coating - dull - 4/5
felt with alkaline perspiration solution ISO 11641	1.000 rubs: slight stainin - grade 4/5 no damage of the coating - dull - 4/5

Flexing Endurance Bally Flex ISO 5402-1: 2011

Method : twbal

2 directions 100.000 cycles - no damage of the coating

Resistance to Blocking ISO BS3424 part 11

result - Blocking, no damage

SAMPLE 20150649102

Your reference : **CABRO 01 CAMEL**

Date of receipt : 22-10-2015

Date analyses : Week 41-45

Sampling by : third party

Place analyses : Servaco

Treatment: Human urine

cleanse - drying at room temperatuur - 4 hours storing at 37°C: 4x this cycle

Conditioning: 16 h 20° C ± 2° - 65 % RH ± 4 %

No visible change -

Martindale abrasion ISO 5470-2: 2003 method 1 - dry to standardwool on treated sample

Method : twmarl Atmosphere for conditioning and testing: 20° C ± 2° - 65 % RV ± 4 %, pressure : 12 kPa

Assessment to ISO 5470-2

1600 rubs	0 rating scale
3200 rubs	0 rating scale
6400 rubs	1 rating scale
12800 rubs	1 rating scale
25600 rubs	1 rating scale
38400 rubs	1 rating scale
51200 rubs	1 rating scale

Rub Fastness Veslic ISO 11640 on treated sample

Method : twves

felt dry	1.000 rubs: slight stainin - grade 4/5 no damage of the coating - colour 5
felt wet	1.000 rubs: slight stainin - grade 4/5 no damage of the coating - dull - 4/5
felt with alkaline perspiration solution ISO 11641	1.000 rubs: slight stainin - grade 4/5 no damage of the coating - dull - 4/5

Flexing Endurance Bally Flex ISO 5402-1: 2011 on treated sample

Method : twbal


2 directions 100.000 cycles - no damage of the coating


Resistance to Blocking ISO BS3424 part 11 on treated sample

result

- slight blocking

Tilly Vandommele
Section Head Textiles




Dr. Nicholas Van Landuyt
General Manager